



Technical Data Sheet

Applications

- Hot melt adhesives
- Packaging
- Wax modification
- Color concentrates

Attributes

- Enhances paraffin wax coating properties like gloss, grease resistance, and MVTR
- Maleic anhydride grafted polyethylene (PE)
- Excellent thermal stability
- Maleic anhydride grafted PE provides functionality
- Improved dispersion in color concentrates

Product Description

EPOLENE® C-29 is a branched low-density polyethylene modified with maleic anhydride. In hot melt adhesives, the maleic anhydride modification allows for improved adhesion, greater filler tolerance, and broader capabilities.

Typical Physical Properties

| Property ^a | Test Method b | Typical Value, Units ^c |
|----------------------------------|---------------|-----------------------------------|
| Density, g/cm ³ | D-1505 | 0.915 |
| Mettler Drop Point, °C | D-6090 | 105 |
| Acid Number, mg KOH/g | D-1386 | 4.0 |
| Brookfield viscosity @125 °C, cP | D-4287 | 800 |
| Yellowness index | E-313 | -2.5 |

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

Packaging

EPOLENE® C-29 is offered in multiple package types. See your Westlake sales or technical representative for packaging offerings and availability.

Storage

The useful life of this product can be affected by storage and handling conditions. This product should be stored in the original unopened container in an enclosed area and protected from moisture, extreme temperatures, and contamination. First-in first-out (FIFO) inventory management is recommended.

Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.