



# Westlake Polymers

Enhancing your life every day

## EF601

Low Density Polyethylene

### Application/Uses

- Heavy duty bags
- Heavy duty shipping sacks
- Industrial shrink film
- Heavy duty C&A sheeting

### Product Description

Westlake EF601 is a fractional melt LDPE with excellent toughness. It is suggested in heavy duty films and shipping sacks, and in industrial shrink applications. It can be used as a bubble stabilizer in LLDPE rich films.

### Typical Physical Properties

<u>Property</u>		<u>Test Method</u>	<u>Typical Value, Units</u>
Melt Index		D 1238	0.25g/10 min
*Density		D 1505	919 kg/m <sup>3</sup> (0.919 g/cm <sup>3</sup> )
Dart Impact		D 1709	250 g/mil
Coefficient of Friction		D 1894	0.5
Ultimate Tensile	MD	D 882	3,500 psi
	TD	D 882	2,700 psi
Ultimate Elongation	MD	D 882	250 %
	TD	D 882	750 %
1% Secant Modulus	MD	D 882	22,000 psi
	TD	D 882	28,000 psi

<sup>a</sup> Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup> Unless noted otherwise, the test method is ASTM.

<sup>c</sup> Units are in SI or US customary units.

### NOTES

Test specimens for blown film: nominal thickness 2.0 mils; blow up ratio 2.5:1, die gap 35 mils.

### FDA

This product has some 21 CFR clearances. Please contact Westlake Product Regulatory Department for statements.

### PROCESSING

Melt temperatures of 360° F – 400° F are recommended for Westlake EF601 with blow-up ratios of 1.5:1 or higher.

### COMMENTS

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given.

*Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

**WESTLAKE CHEMICAL CORPORATION**  
2801 Post Oak Blvd Suite 600 Houston, Texas  
Customer Service: 1-800-545-9577