

#### **Technical Data Sheet**

# **Applications**

- Compounding base resin
- Color concentrates
- Additives masterbatches

## **Product Description**

Westlake EF608 is a high melt index LDPE resin suggested for thin gauge garment films and other films requiring excellent drawdown. The high melt index also makes this material a good choice in compounding applications as a carrier for masterbatch or other concentrates.

### **Typical Physical Properties**

Property a		Test Method b	Typical Value, Units <sup>c</sup>
Melt Index (Condition 190°C/2.16 kg)		D 1238	9.5 g/10 min
Density (Base Formulation)		D 1505	919 kg/m³ (0.919 g/cm³)
Dart Impact		D 1709	80 g/mil
Tensile Strength @ Break	M.D. T.D.	D 882 D 882	20.7 MPa (3,000 psi) 15.2 MPa (2,200 psi)
Elongation @ Break	M.D. T.D.	D 882 D 882	340 % 750 %
1% Secant Modulus	M.D. T.D.	D 882 D 882	144.8 MPa (21,000 psi) 172.4 MPa (25,000 psi)

<sup>&</sup>lt;sup>a</sup> Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

#### Notes

Test specimens for blown film: nominal thickness 2.0 mils; blow up ratio 2.5:1, die gap 35 mils.

## **Processing**

Melt temperatures of 360°F – 400°F are recommended for Westlake EF608 with blow-up ratios of 1.5:1 or higher.

# **Regulatory Compliance**

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

<sup>&</sup>lt;sup>b</sup> Unless noted otherwise, the test method is ASTM.

<sup>&</sup>lt;sup>c</sup> Units are in SI or US customary units.