



Application/Uses

- Injection Molding
- Compounding
- Foam

Product Description

Westlake ELEVATE™ EM518AA is an ethylene vinyl acetate copolymer with 18.5% VA. EM518AA is designed for use in applications such as injection molding, compounding, foaming, and general extrusion. This material has excellent low temperature brittleness properties, melt strength, and flexibility.

Typical Physical Properties

<u>Property</u> ^a	<u>Test Method</u> ^b	<u>Typical Value, Units</u> ^c
Melt Index	D 1238	2.50 g/10 min
Density	D 1505	940 kg/m ³ (0.940 g/cm ³)
Peak Melt Temp	Westlake Method	86°C (187°F)
Vicat Softening Point	D 1525	68°C (154°F)
Ultimate Tensile @ Break	D 638	1745 PSI
Elongation	D 638	645 %
Flexural Modulus, 1% Secant	D 790	7000 PSI
Hardness, 15s Shore D	D 2240	32

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

NOTES

Physical properties measured on compression molded specimens.

FDA

Please contact Product Regulatory Compliance (903-242-7683).

PROCESSING

Please contact Westlake Technical Services for specifics on processing temperatures.

NOTICE

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

WESTLAKE CHEMICAL CORPORATION
2801 Post Oak Blvd Suite 600 Houston, Texas
Customer Service: 1-88-545-9577