



## Application/Uses

- Shrink film
- Frozen food packaging

## Product Description

WESTLAKE polyethylene EN1807 is a fractional-melt low-density formulation suggested for film applications requiring high impact strength, high tear strength, and very good optical properties, such as packaging for frozen foods.

## Typical Physical Properties

<u>Property<sup>a</sup></u>		<u>Test<sup>b</sup> Method</u>	<u>Typical Value, Units<sup>c</sup></u>
Melt Index (Condition 190°C/2.16 kg)		D 1238	0.7 g/10 min
Density		D 4883	921 kg/m <sup>3</sup> (0.921 g/cm <sup>3</sup> )
Haze		D 1003	4.0%
Gloss @ 45°		D 2457	80
Impact		D 1709A	110 g
Tensile Strength @ Break	M.D.	D 882	33 MPa (4800 psi)
	T.D.	D 882	22 MPa (3100 psi)
Elongation (%)	M.D.	D 882	200%
	T.D.	D 882	800%
1% Secant Modulus	M.D.	D 882	220 MPa (32000 psi)
	T.D.	D 882	274 MPa (40000 psi)

<sup>a</sup> Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup> Unless noted otherwise, the test method is ASTM.

<sup>c</sup> Units are in SI or US customary units.

## NOTES

Test specimens for blown film: nominal thickness 1.5 mils; blow up ratio 2.4:1, die gap 50 mils.

## FDA

This product has some 21 CFR clearances. Please contact Westlake Product Regulatory Department for statements.

## PROCESSING

Melt temperatures of 360° F – 380° F are recommended for Westlake EN1807 with blow-up ratios of 2.4:1 or higher.

## COMMENTS

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given.

*Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

**WESTLAKE CHEMICAL CORPORATION**  
2801 Post Oak Blvd Suite 600 Houston, Texas  
Customer Service: 1-800-545-9577