



## Application/Uses

- Blown film extrusion
- Heavy Duty Films

## Product Description

Westlake HIFOR Xtreme® SC74884 is an enhanced hexene LLDPE designed for blown film extrusion applications requiring high strength and toughness. Westlake HIFOR Xtreme® SC74884 contains no slip or anti-block. This material is highly stabilized and contains process aid.

## Typical Physical Properties

<u>Property</u>		<u>Test Method</u>	<u>Typical Value, Units</u>
Melt Index		D 1238	0.75 g/10 min
Density		D 1505	9150 kg/m <sup>3</sup> (0.915 g/cm <sup>3</sup> )
Haze		D 1003	12.0%
Gloss@45°		D 2457	62.0%
Dart Impact		D 1709	750 grams
Tensile Break	MD	D 882	7,600 psi
	TD	D 882	5,000 psi
Ultimate Elongation	MD	D 882	700 %
	TD	D 882	950 %
1% Secant Modulus	MD	D 882	25,000 psi
	TD	D 882	28,000 psi

Typical film property as measured on 1.0 mil film from blown film extruder.

**NOTES: Kosher Compliant.**

## FDA

This product has some 21 CFR clearances. Please contact Westlake Product Regulatory Department for statements.

## PROCESSING

Blown film extrusion melt temperatures of 400° – 430° F are recommended for Westlake Chemical HIFOR Xtreme® SC74884.

## NOTICE

The data listed represents typical values as measured by Westlake Chemical Corporation. They are given for information only, and not guarantee of their accuracy is made. The product is sold upon condition that purchasers shall make their own tests to determine the characteristics of the product and the suitability of the product for their particular purpose.

Westlake makes no representation or warranty of any kind, express or implied, with respect to this product, whether as to merchantability, fitness for particular purpose or otherwise.

*Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*