

## Applications

- Compounding
- Emulsions
- Hot melt adhesives

## Attributes

- Coupling agent and compatibilizer for PP composites
- Excellent pigment dispersion aid
- Provides slip resistance in floor polish
- Maleic anhydride grafted polypropylene (PP) powder
- High level of maleic graft functionality

## Product Description

EPOLENE® E-43P is a chemically modified polypropylene powder used as a coupling agent for polypropylene composites and for providing slip resistance in floor finish emulsions. Because of the polarity and anhydride functionality, EPOLENE® E-43P polymer is useful for laminating, as a compatibilizer for PP blends with nylon or EVOH, and for enhancing the strength of composites that utilize reinforcements / fillers such as glass, talc, calcium carbonate, and metals.

## Typical Physical Properties

Property <sup>a</sup>	Test Method <sup>b</sup>	Typical Value, Units <sup>c</sup>
Acid Number	D-1386	40-55 mg-KOH/g
Penetration Hardness	D-5	<1 dmm
Mettler Softening Point, °C	D-6090	153-162 °C
Brookfield Viscosity @ 190 °C	D-4287	150-700 cP
Yellowness Index	E-313	≤ 70.0
Median Particle Size	Westlake	215 microns

<sup>a</sup> Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup> Unless noted otherwise, the test method is ASTM.

<sup>c</sup> Units are in SI or US customary units.

## Packaging

EPOLENE® E-43P is offered in multiple package types. See your Westlake sales or technical representative for packaging offerings and availability.

## Storage

The useful life of this product can be affected by storage and handling conditions. This product should be stored in the original unopened container in an enclosed area and protected from moisture, extreme temperatures, and contamination. First-in first-out (FIFO) inventory management is recommended.

## Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

*Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*