

Applications

- Frozen food packaging
- Fresh food packaging
- Ice bags
- Heavy duty produce bags

Product Description

EB561 resin is a fractional melt index 6.5% vinyl acetate copolymer designed for ice bags, frozen food bags, and other films that require excellent toughness and good heat sealing characteristics. This resin has excellent low temperature brittleness properties.

Typical Physical Properties

| Property ^a | | Test Method ^b | Typical Value, Units ^c |
|----------------------------|------|--------------------------|--|
| Melt Index | | D 1238 | 0.55 g/10 min |
| Density | | D 1505 | 929 kg/m ³ (0.929 g/cm ³) |
| Haze | | D 1003 | 4.8% |
| Gloss @ 45° | | D 2457 | 74 |
| Dart Impact | | D 1709 | 480 g |
| Tensile Strength @ Break | M.D. | D 882 | 24.1 MPa (3,500 psi) |
| | T.D. | D 882 | 25.5 MPa (3,700 psi) |
| Tensile Elongation @ Break | M.D. | D 882 | 380% |
| | T.D. | D 882 | 550% |
| 1% Secant Modulus | M.D. | D 882 | 103.4 MPa (15,000 psi) |
| | T.D. | D 882 | 110.3 MPa (16,000 psi) |

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

Notes

Test specimens for blown film: nominal thickness 1.25 mils; blow up ratio 2.5:1, die gap 35 mils.

Processing

Melt temperatures of 360°F – 390°F are recommended for EB561 with blow-up ratios of 1.5:1 or higher.

Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.