

## Applications

- Flexible medical
- Food packaging
- Laminating
- Playing cards
- Toys / sporting goods

## Product Description

TRUCOAT® EC1550 is a low density polyethylene resin designed for use in extrusion coating applications, especially when increased heat-seal range is needed.

## Typical Physical Properties

Property <sup>a</sup>	Test Method <sup>b</sup>	Typical Value, Units <sup>c</sup>
Melt Index	D 1238	3.5 g/10 min
Density	D 4883	917 kg/m <sup>3</sup> (0.917 g/cm <sup>3</sup> )
Peak Melting Point by DSC	D 3418	107°C (225°F)
Vicat Softening Point	D 1525	87°C (189°F)
Ultimate Tensile 500 mm/min (20 in/min)	D 638 Type IV Specimen	1,800 psi
Elongation 500 mm/min (20 in/min)	D 638 Type IV Specimen	400%
Flexural Modulus 1% Secant	D 790	28,000 psi

<sup>a</sup> Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup> Unless noted otherwise, the test method is ASTM.

<sup>c</sup> Units are in SI or US customary units.

## Notes

Where required, test specimens are compression molded according to ASTM D 1928.

## Processing

Extrusion coating melt temperatures not to exceed 625°F are recommended for TRUCOAT® EC1550.

## Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

---

*Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*