

## **Technical Data Sheet**

# **Applications**

- Food packaging
- Freezer wrap
- Frozen food packaging
- Sugar Pouches

#### **Product Description**

TRUCOAT® EC4042 is a low density polyethylene resin designed for extrusion coating applications, such as sugar pouches and freezer wrap, where high coating speeds and good drawdown are required. This product also provides good heat seals at high packaging or sealing rates.

## **Typical Physical Properties**

Property <sup>a</sup>	Test Method <sup>b</sup>	Typical Value, Units <sup>c</sup>
Melt Index	D 1238	10.0 g/10 min
Density	D 1505	917 kg/m³ (0.917 g/cm³)
Peak Melting Point by DSC (Tm)	D 3418	105.2°C (221.4°F)
Vicat Softening Temperature	D 1525	85°C (185°F)
Tensile Strength @ Break (500 mm/min, 20 in/min)	D 638 Type IV Specimen	10.3 MPa (1,500 psi)
Elongation @ Break (500 mm/min, 20 in/min)	D 638 Type IV Specimen	400 %
Flexural Modulus 1% Secant	D 790	193 MPa (28,000 psi)

<sup>&</sup>lt;sup>a</sup> Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

#### Notes

Where required, test specimens are compression molded according to ASTM D 1928.

# Processing

Extrusion coating melt temperatures not to exceed 625°F are recommended for TRUCOAT® EC4042.

# **Regulatory Compliance**

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

<sup>&</sup>lt;sup>b</sup> Unless noted otherwise, the test method is ASTM.

<sup>&</sup>lt;sup>c</sup> Units are in SI or US customary units.