

Applications

- High clarity packaging
- Light and medium duty produce bags
- Linear blend component for sealing and clarity

Product Description

ELEVATE® EF437 is a 2.5% vinyl acetate copolymer designed for films that require excellent optical and strength properties. This resin has excellent heat sealing characteristics and low temperature brittleness properties.

Typical Physical Properties

Property ^a		Test Method ^b	Typical Value, Units ^c
Melt Index (Condition 190°C/2.16 kg)		D 1238	2.0 g/10 min
Density		D 1505	925 kg/m ³ (0.925 g/cm ³)
Haze		D 1003	3.3%
Gloss @ 45°		D 2457	79
Dart Impact		D 1709A	150 g
Tensile Strength @ Break	M.D.	D 882	24.1 MPa (3,500 psi)
	T.D.	D 882	17.2 MPa (2,500 psi)
Tensile Elongation @ Break	M.D.	D 882	350%
	T.D.	D 882	700%
1% Secant Modulus	M.D.	D 882	137.9 MPa (20,000 psi)
	T.D.	D 882	151.7 MPa (22,000 psi)

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

Notes

Test specimens for blown film: nominal thickness 1.25 mils; blow up ratio 2.5:1, die gap 35 mils.

Processing

Melt temperatures of 360°F – 390°F are recommended for EF437 with blow-up ratios of 1.5:1 or higher.

Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.