

Technical Data Sheet

Applications

- High Clarity Flexible Packaging
- High Impact Films

Product Description

ELEVATE® EF439 is a 4% vinyl acetate copolymer. It produces films with excellent haze, gloss, impact strength, and very good heat seal.

Typical Physical Properties

Property ^a		Test Method ^b	Typical Value, Units ^c
Melt Index		D 1238	1.4 g/10 min
Density		D 1505	926.5 kg/m ³ (0.9265 g/cm ³)
Haze		D 1003	4.4%
Gloss @ 45°		D 2457	72
Dart Impact		D 1709	250 g
Tensile Strength @ Break	M.D.	D 882	27.6 MPa (4,000 psi)
	T.D.	D 882	21.4 MPa (3,100 psi)
Tensile Elongation @ Break	M.D.	D 882	300%
	T.D.	D 882	600%
1% Secant Modulus	M.D.	D 882	144.8 MPa (21,000 psi)
	T.D.	D 882	179.3 MPa (26,000 psi)

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

Notes

Test specimens for blown film: nominal thickness 1.25 mils; blow up ratio 2.5:1, die gap 35 mils.

Processing

Melt temperatures of 360°F – 390°F are recommended for EF439 with blow-up ratios of 1.5:1 or higher.

Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.