



Application/Uses

- Flexible packaging films
- Peelable seals, adhesive layers
- Injection and blow molding
- Profile extrusions, tubing, wire & cable

Product Description

Westlake ELEVATE™ EF528AA is an ethylene vinyl acetate copolymer with 18.5% VA. EF528AA is designed for blown and cast films requiring excellent optics and low heat seal initiation. High melt strength makes EF528AA an excellent choice for profile extrusions, molding, and foaming applications requiring medium VA content.

Typical Physical Properties

Property		Test Method	Typical Value, Units
Melt Index		D 1238	2.5 g/10 min
Density		D 1505	940 kg/m ³ (0.940 g/cm ³)
Haze		D 1003	3.6 %
Gloss @ 45°		D 2457	82
Ultimate Tensile	MD	D 638	3,600 psi
	TD	D 638	3,500 psi
1% Secant Modulus	MD	D 882	6,100 psi
	TD	D 882	7,300 psi
Elongation	MD	D 882	600%
	TD	D 882	800%
Dart Impact		D1709	290 grams
DSC Peak Melting Temperature		D 3418	85°C (185°F)
Vicat Softening Point		D 1525	67°C (153°F)

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

Typical film property as measured on a 1.25 mil blown film sample fabricated at a 2.5:1 B.U.R.

*AA formulation contains no slip and no antiblock.

FDA

This resin grade complies with 21 CFR, section 177.1350. For further information, please contact Product Regulatory Compliance.

PROCESSING

A blown film melt temperature not to exceed 350° F and a cast film melt temperature not to exceed 400° F is recommended for ELEVATE™ EF528AA.

NOTICE

The data listed represents typical values as measured by Westlake Chemical Corporation. They are given for information only, and not guarantee of their accuracy is made. The product is sold upon condition that purchasers shall make their own tests to determine the characteristics of the product and the suitability of the product for their particular purpose.

Westlake makes no representation or warranty of any kind, express or implied, with respect to this product, whether as to merchantability, fitness for particular purpose or otherwise.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.