

ELEVATE® EF529

Ethylene Vinyl Acetate Copolymer

Applications

- Flexible packaging films
- Peelable seals & adhesive layers
- Injection molding
- Profile extrusion and tubing

Product Description

ELEVATE® EF529 is an 18.5% vinyl acetate copolymer designed for flexible packaging that requires excellent optical properties and low heat seal initiation temperature. It is also suitable for profile extrusion, molding, and foam applications.

Typical Physical Properties

Property ^a	-	Test Method ^b	Typical Value, Units ^c
Melt Index (Condition 190°C/2.16 kg)		D 1238	2.5 g/10 min
Density		D 1505	940 kg/m³ (0.940 g/cm³)
DSC Melting Point		D 3418	85°C (185°F)
Vicat Softening Point		D 1525	67°C (153°F)
Haze		D 1003	3.6%
Gloss @ 45°		D 2457	82
Dart Impact		D 1709	290 g
Tensile Strength @ Break	M.D. T.D.	D 882 D 882	24.8 MPa (3,600 psi) 24.1 MPa (3,500 psi)
Elongation @ Break	M.D. T.D.	D 882 D 882	600% 800%
1% Secant Modulus	M.D. T.D.	D 882 D 882	42.1 MPa (6,100 psi) 50.3 MPa (7,300 psi)

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

Notes

Test specimens for blown film: nominal thickness 1.25 mils; blow up ratio 2.5:1, die gap 35 mils.

Processing

Melt temperatures of 360°F – 390°F are recommended for EF529 with blow-up ratios of 1.5:1 or higher.

Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

Westlake Polymers LLC

2801 Post Oak Boulevard, Suite 600 Houston, Texas 77056 1.800.545.9577 www.westlake.com

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.