

Applications

- Diaper liners
- General purpose clarity
- Multi-layered packaging films

Product Description

Westlake EG378 LDPE is suggested for cast film applications. It has excellent haze and gloss, good strength, good processability, and good heat sealability. This Kosher-compliant resin is enhanced with an increased stabilization package for excellent thermal stability during processing.

Typical Physical Properties

Property ^a		Test Method ^b	Typical Value, Units ^c
Melt Index		D 1238	4.0 g/10 min
Density		D 1505	922 kg/m ³ (0.922 g/cm ³)
Haze		D 1003	5.5%
Gloss @ 45°		D 2457	70
Dart Impact		D 1709	80 g/mil
Ultimate Tensile	M.D.	D 882	3,500 psi
	T.D.	D 882	2,700 psi
Elongation	M.D.	D 882	350%
	T.D.	D 882	700%
1% Secant Modulus	M.D.	D 882	25,000 psi
	T.D.	D 882	29,000 psi

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

Notes

Test specimens for blown film: nominal thickness 1.25 mils; blow up ratio 2.5:1, die gap 35 mils.

Processing

Melt temperatures of 360°F – 400°F are recommended for Westlake EG378 with blow-up ratios of 1.5:1 or higher.

Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product, and nothing herein waives any of the Seller's conditions of sale.