



# Westlake Polymers

Enhancing your life every day

## EM811

EM811AA = 811A or 811E

### Application/Uses

- Flexible medical
- Medical

### Product Description

WESTLAKE low-density polyethylene EM811 is a low-density formulation used for injection molding. It is characterized by high flow and low stiffness.

### Typical Physical Properties

<u>Property</u> <sup>a</sup>	<u>Test Method</u> <sup>b</sup>	<u>Typical Value, Units</u> <sup>c</sup>
Melt Index	D 1238	20.0g/10 min
Density	D 4883	916 kg/m <sup>3</sup> (0.916 g/cm <sup>3</sup> )
Tensile Stress @ Break 500 mm/min (20 in./min)	D 638 Type IV Specimen	9 MPa (1300 psi)
Elongation @ Break 500 mm/min (20 in./min)	D 638 Type IV Specimen	300%

<sup>a</sup> Unless noted otherwise, all test are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup> Unless noted otherwise, the test method is ASTM.

<sup>c</sup> Units are in SI or US customary units.

#### NOTES:

WESTLAKE low-density polyethylene EM811 is a low-density formulation used for injection molding. It is characterized by high flow and low stiffness.

#### FDA

This product has some 21 CFR clearances. Please contact Westlake Product Regulatory Department for statements.

#### NOTICE

The data listed represents typical values as measured by Westlake. They are given for information only, and not guarantee of their accuracy is made. The product is sold upon condition that purchasers shall make their own tests to determine the characteristics of the product and the suitability of the product for their particular purpose.

Westlake makes no representation or warranty of any kind, express or implied, with respect to this product, whether as to merchantability, fitness for particular purpose or otherwise.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.