

Applications

- Converter film for food / industrial packaging
- Flexible medical
- Injection molding

Product Description

Westlake EN1817 is an LDPE resin suggested for injection molding applications and film applications requiring high clarity, good tear and impact strength, good printability, and a wide heat-sealing range.

Typical Physical Properties

Property ^a		Test Method ^b	Typical Value, Units ^c
Melt Index		D 1238	1.7 g/10 min
Density		D 4883	920 kg/m ³ (0.920 g/cm ³)
Peak Melting Point by DSC		D 3418	112.0°C (233.6°F)
Haze		D 1003	6.0%
Gloss @ 45°		D 2457	70
Dart Impact		D 1709	110 g/mil
Ultimate Tensile	M.D.	D 882	4,900 psi
	T.D.	D 882	3,200 psi
Elongation	M.D.	D 882	300%
	T.D.	D 882	850%
1% Secant Modulus	M.D.	D 882	30,000 psi
	T.D.	D 882	35,000 psi

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

Notes

Test specimens for blown film: nominal thickness 1.5 mils; blow up ratio 2.4:1, die gap 50 mils.

Processing

Melt temperatures of 360°F – 400°F are recommended for Westlake EN1817 with blow-up ratios of 2.4:1 or higher.

Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product, and nothing herein waives any of the Seller's conditions of sale.