

Technical Data Sheet

Applications

- Blown and cast films
- Tie-layer

Product Description

TYMAX® GT4300 is a maleic anhydride modified linear low density polyethylene designed for blown and cast film applications. It has a high level of maleic anhydride modification to allow it to be utilized for blending in tailor-made tie layers for multilayer film applications. TYMAX® GT4300 is designed for bonding to polyolefins, polyamides, and EVOH film layers. It does not contain any slip or antiblock additives.

Typical Physical Properties

Property ^a	Test Method ^b	Typical Value, Units ^c
Melt Index	D 1238	8.0 g/10 min
Density	D 4883	918 kg/m ³ (0.918 g/cm ³)
DSC Melting Point	D 3418	121°C (250°F)
DSC Crystallization Point	D 3418	106°C (223°F)

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

Processing

Melt temperatures of 390°F – 420°F are recommended for TYMAX® GT4300. For assistance with applications and temperature profiles, please contact your Westlake Technical Services Representative.

Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.