

Applications

- Extrusion coating
- Laminations
- Tie-layer

Product Description

TYMAX[®] GT7501 is a maleic anhydride modified ethylene methyl acrylate copolymer designed for use as a tie layer in extrusion coating and lamination applications. GT7501 is suitable for adhesion to polyolefins, polyamides, and PET in multilayer film structures.

Typical Physical Properties

Property ^a	Test Method ^b	Typical Value, Units ^c
Melt Index (Condition 190°C/2.16 kg)	D 1238	7.0 g/10 min
Density	D 4883	942 kg/m ³ (0.942 g/cm ³)
Methyl Acrylate Content	Westlake	20 weight %
Vicat Softening Point	D 1525	46°C (115°F)
Durometer Hardness, Shore D	D 2240	36
DSC Melting Point	D 3418	96°C (205°F)

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

Processing

Extrusion coating melt temperatures not to exceed 625°F are recommended for TYMAX[®] GT7501. For assistance with applications and temperature profiles, please contact your Westlake Technical Services Representative.

Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.