

Applications

- Cast film extrusion
- Cast stretch film

Product Description

HIFOR® LF2051 is a hexene LLDPE designed for cast film extrusion. HIFOR® LF2051 contains stabilization ideal for the cast extrusion process.

Typical Physical Properties

Property ^a		Test Method ^b	Typical Value, Units ^c
Melt Index		D 1238	3.5 g/10 min
Density (Base Formulation)		D 1505	918 kg/m ³ (0.918 g/cm ³)
Dart Impact		D 1709	95 g/mil
Haze (Base Formulation)		D 1003	1.5%
Elmendorf Tear	M.D.	D 1922	300 g/mil
	T.D.	D 1922	700 g/mil
Ultimate Tensile	M.D.	D 882	7,300 psi
	T.D.	D 882	4,900 psi
Elongation	M.D.	D 882	500%
	T.D.	D 882	850%
1% Secant Modulus	M.D.	D 882	20,000 psi
	T.D.	D 882	22,000 psi

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

Processing

Cast extrusion melt temperatures of 500°F – 540°F are recommended for HIFOR® LF2051.

Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.