



## Application/Uses

- Photographic paper
- Release paper
- Spiral wound can linings
- Grease barrier

## Product Description

Westlake MC3033 is a high density polyethylene designed for extrusion coating and lamination applications. MC3033 provides improved barrier properties, temperature resistance, stress crack resistance, scuff resistance, gloss and coefficient of friction (COF) compared to low density polyethylene.

## Typical Physical Properties

<u>Property<sup>a</sup></u>	<u>Test<sup>b</sup> Method</u>	<u>Typical Value, Units<sup>c</sup></u>
Melt Index (Condition 190°C/2.16 kg)	D 1238	10 g/10 min
Density	D 4883	947 kg/m <sup>3</sup> (0.947 g/cm <sup>3</sup> )
Vicat Softening Temperature	D 1525	117°C (243°F)
Brittleness Temperature	D 1525	<-73°C (<-99°F)
Tensile Stress @ Break 500 mm/min (20 in./min)	D 638	24.5 MPa (3555 psi)
Elongation @ Break 500 mm/min (20 in./min)	D 638	13.5%
Melt Index (Condition 190°C/2.16 kg)	D 1238	10 g/10 min

<sup>a</sup> Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup> Unless noted otherwise, the test method is ASTM.

<sup>c</sup> Units are in SI or US customary units.

## Notes

Where required, specimens are compression molded according to ASTM D1928.

## FDA

This resin grade complies with 21 CFR 177.1520. For further information, please contact Product Regulatory Compliance.

## Processing

Contact the Westlake Chemical Corporation Technical Services Group for processing temperature information. (903-242-7693)

## Comments

Properties reported here are typical of average lots. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.