

## Technical Data Sheet

### Applications

- Compounding
- Hot Melt Adhesives
- Packaging
- Solvent-based coatings
- Wax modification

### Attributes

- Improves blocking, scuff and abrasion resistance in paraffin wax blends
- Useful in color concentrates, toner compounds, and as a pigment dispersion aid
- Low molecular weight
- Polypropylene homopolymer

### Product Description

EPOLENE® N-15 is a low viscosity polypropylene homopolymer with a high melt point and excellent hardness.

### Typical Physical Properties

Property <sup>a</sup>	Test Method <sup>b</sup>	Typical Value, Units <sup>c</sup>
Density, g/cm <sup>3</sup>	D-1505	0.902
Penetration Hardness, dmm	D-5	< 1
Mettler Drop Point, °C	D-6090	164
Brookfield Viscosity @ 190 °C, cP	D-4287	590
Yellowness Index	E-313	8.0

<sup>a</sup> Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup> Unless noted otherwise, the test method is ASTM.

<sup>c</sup> Units are in SI or US customary units.

### Packaging

EPOLENE® N-15 is offered in multiple package types. Contact your Westlake sales or technical representative for offerings and availability.

### Storage

The useful life of this product can be affected by storage and handling conditions. This product should be stored in the original unopened container in an enclosed area and protected from moisture, extreme temperatures, and contamination. First-in first-out (FIFO) inventory management is recommended.

### Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

*Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*