

## Applications

- Asphalt modification
- Hot melt adhesives
- Compounding
- Solvent based coatings
- Wax modification
- Wire and cable

## Attributes

- Higher melt point and hardness provides improved resistance to solvents / oils
- Improved slump resistance in cable filling and flooding
- Provides lubricity in printing inks
- Useful as a viscosity modifier in hot melt adhesives
- Medium density polyethylene

## Product Description

EPOLENE<sup>®</sup> N-21 is a non-emulsifiable medium density polyethylene that improves slump resistance in cable filling and flooding, provides lubricity in printing inks, and as a viscosity modifier in hot melt adhesives. Its higher melting point and hardness, compared to other EPOLENE<sup>®</sup> N type polymers, provides improved resistance to solvents and oils.

## Typical Physical Properties

Property <sup>a</sup>	Test Method <sup>b</sup>	Typical Value, Units <sup>c</sup>
Penetration Hardness	D-5	<1 dmm
Mettler Drop Point	D-6090	117-123 °C
Brookfield Viscosity @ 150 °C	D-4287	250-450 cP
Yellowness Index	E-313	≤ 1.0

<sup>a</sup> Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup> Unless noted otherwise, the test method is ASTM.

<sup>c</sup> Units are in SI or US customary units.

## Packaging

EPOLENE<sup>®</sup> N-21 is offered in multiple package types. See your Westlake sales or technical representative for packaging offerings and availability.

## Storage

The useful life of this product can be affected by storage and handling conditions. This product should be stored in the original unopened container in an enclosed area and protected from moisture, extreme temperatures, and contamination. First-in first-out (FIFO) inventory management is recommended.

## Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

*Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*