

Applications

- Films – blown and cast
- Disposable gloves & instrument covers
- Medical drapes
- Silk/quiet Films

Key Attributes

- Low coefficient of friction
- Fully formulated with slip & antiblock
- Softness & flexibility

Product Description

EMAC+[®] SP1358 is a 21.5% EMA copolymer containing slip and antiblock. This resin is designed for blown or cast film where flexibility and low C.O.F. are required. The higher melting point of this EMAC+[®] grade offers EMA performance with improved heat resistance.

Typical Physical Properties

Property ^a	Test Method ^b	Typical Value, Units ^c
Methyl Acrylate Content	Westlake	21.5 weight %
Melt Index (Condition 190°C/2.16 kg)	D 1238	2.6 g/10 min
Density	D 1505	948 kg/m ³ (0.948 g/cm ³)
Vicat Softening Temperature	D 1525	44°C (111°F)
Durometer Hardness Shore D Scale	D 2240	32
Haze	D 1003	15%
Gloss @ 45°	D 2457	45
Dart Impact	D 1709A	400 g
Elmendorf Tear Resistance (MD / TD)	D 1922	70 gf/ 170gf
Film Tensile Strength @ Break (MD / TD)	D 882	16.5 MPa (2400 psi) / 13.8 MPa (2000 psi)
Film Tensile Elongation @ Break (MD / TD)	D 882	500% / 750%
Film Tensile Modulus, 1% Secant (MD / TD)	D 882	38.6 MPa (5600 psi) / 28.3 MPa (4100 psi)

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units

Notes

Methyl acrylate copolymers are soft, pliable, and tough at ambient and freezing temperatures. They exhibit high solids filling capability and compatibility with a wide range of polymers, facilitating their use as concentrate bases.

Processing

Processing conditions for methyl acrylate copolymer resins vary depending upon application, fabrication equipment, and other resin use. These resins are thermally stable and process like LDPE.

Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

Westlake Polymers LLC

2801 Post Oak Boulevard, Suite 600

Houston, Texas 77056

1.800.545.9577

www.westlake.com