

## Technical Data Sheet

### Applications

- Masterbatches/compounding
- Extrusion coating/laminations
- Carpet backing

### Key Attributes

- Low viscosity
- Compatibility with many polymers
- Highly fillable

### Product Description

EMAC® SP2220 is a 20% ethylene methyl acrylate (EMA) copolymer designed for compounding, extrusion coating, tie-layers, and extrusions where flexibility, compatibility, low heat seal temperatures, or high coefficient of friction are required. EMAC® SP2220 is compatible with and provides excellent adhesion to polyolefins, polyesters, and other polymers while providing outstanding low temperature performance. EMAC® SP2220 is an excellent universal masterbatch resin.

### Typical Physical Properties

Property <sup>a</sup>	Test Method <sup>b</sup>	Typical Value, Units <sup>c</sup>
Methyl Acrylate Content	Westlake	20 weight %
Melt Index (Condition 190°C/2.16 kg)	D 1238	20.0 g/10 min
Density	D 1505	941 kg/m <sup>3</sup> (0.941 g/cm <sup>3</sup> )
Vicat Softening Temperature	D 1525	47°C (117°F)
Melting Point by DSC (T <sub>m</sub> )	D 3418	83°C (181°F)
Brittleness Temperature	D 746	< -42°C (< -44°F)
Durometer Hardness Shore D Scale	D 2240	36
Tensile Stress @ Break (500 mm/min, 20 in/min)	D 638 Type IV	7 MPa (1,000 psi)
Elongation @ Break (500 mm/min, 20 in/min)	D 638 Type IV	675%

<sup>a</sup> Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup> Unless noted otherwise, the test method is ASTM.

<sup>c</sup> Units are in SI or US customary units.

### Notes

The reported properties were measured from compression molded specimens prepared according to ASTM D 1928.

### Processing

Processing conditions for methyl/butyl acrylate copolymer resins vary depending upon application, fabrication equipment, and other resin use. These resins are thermally stable and process like LDPE.

### Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

*Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*